



PALLADIUM Textured Coating is a proprietary blend of latex acrylics formulated to provide an elastomeric, resilient, stucco-like finish with superior weathering characteristics.



Sealants & Coatings
Technologies, Inc.
106 Industrial Way
Charlestown, IN 47111

1-800-899-3301
Fax: 812-256-2344

■ BASIC USE

PALLADIUM Textured Coating is designed for use over wood, OSB, cementitious surfaces, structural insulated panels, urethane foam sheathing, foam form blocks, existing stucco, masonry and aged wood.

■ LIMITATIONS

PALLADIUM Textured Coating must be applied to structurally sound, solid, clean and dry substrates. It should not be applied to loose, crumbly, chalky or smooth plastic surfaces. Surface must also be free of any oil, solvent or asphalt impregnated materials or oil-based finishes of any kind.

■ ADVANTAGES

- Flexible - forms continuous seamless coating.
- Textured appearance that can be troweled or sprayed in a variety of stucco-appearing finishes.
- Water-resistant - withstands wind-driven rain, salt spray and most chemicals.
- Excellent weatherability and color retention.
- Low maintenance requirements.
- Excellent adhesion.
- Odorless when cured.
- Water clean up.
- Resists mold and mildew.
- Variety of earth-tone colors.
- Excellent paintable surface.

■ TECHNICAL INFORMATION

Texture

Medium. Secondary textures applied over base coat include skip trowel, knock down, quartz putz.

Recommended Thickness

60 - 80 mils.

Coverage

100 to 130 square feet per 5 gallon pail.

Drying Time

Tack free 1 hour, complete cure 72 hours depending upon weather conditions and composition/porosity of substrate.

Recommended Primers

Ferrous Metal

Rust resistant latex primer.

Concrete

SCT Sealing Primer.

Colors

Arctic White, Sandalwood, Desert Sunrise, Sandstone, Southern Gray, Smoke Gray, Sierra Tan, Palomino Beige and Hawaiian Sand.

Packaging

5 gallon pail, 50 lbs.

Storage

Store PALLADIUM Textured Coating in cool dry space in temperatures ranging between 40° F. and 90° F. DO NOT ALLOW MATERIAL TO FREEZE OR SIT IN SUN OR OTHER AREAS WHERE TEMPERATURES MAY EXCEED 90° F.

Shelf Life

12 months stored in unopened container at temperatures between 40° F. and 90° F.

■ APPLICATION GUIDELINES

PALLADIUM Textured Coating may only be installed by professional stucco applicators who are FACTORY TRAINED AND CERTIFIED TO USE THIS PRODUCT. The only exception to this is when PALLADIUM Textured Coating is used specifically for coating of foundations. In this case, the user is solely responsible for determining the suitability of this product for its intended use prior to application.

For all other applications, PALLADIUM Textured Coating must be applied in strict accordance with the PALLADIUM Textured Coating Application Manual published by SEALANTS & COATINGS TECHNOLOGIES, INC. NO OTHER EXCEPTIONS WILL BE ALLOWED. THIS APPLICATION MANUAL IS PRESENTED ONLY WHEN ATTENDING THE TRAINING AND CERTIFICATION SEMINAR.

General Instruction for Application to Foundations

Surface Preparation

The foundation surface must be struc-

turally sound, solid, clean and dry. PALLADIUM Textured Coating should not be applied to loose, crumbly, chalky or smooth plastic surfaces. The surface should also be completely free of any oil, solvent or asphalt impregnated materials or oil-based finishes of any kind.

Application Temperatures

PALLADIUM Textured Coating should be applied when ambient temperatures range between 40° F. and 90° F. and when relative humidity does not exceed 90%. DO NOT ATTEMPT TO APPLY PRODUCT IF FREEZING TEMPERATURES ARE EXPECTED WITHIN 72 HOURS. DO NOT APPLY PRODUCT DURING RAIN OR WHEN RAIN IS IMMINENT. IF RAIN OR OTHER INCLEMENT WEATHER IS EXPECTED WITHIN 72 HOURS AFTER MATERIAL HAS BEEN APPLIED, PLASTIC SHEETING SHOULD BE USED TO PROTECT FRESHLY APPLIED COATING.

MAINTENANCE

No particular maintenance is required. However, should any cracks or separations occur because of excessive substrate movement or other unusual circumstances, simply apply material into cracks or separations and texture as appropriate. PALLADIUM Textured Coating may also be lightly hosed to remove dust and dirt.

AVAILABILITY/SUPPORT

Palladium Textured Coating is available from the manufacturing plant in Charlestown, IN (800-899-3301), our Distribution Center in New Castle, CO (800-430-7074), as well as a national network of distributors. Sealants & Coatings Technologies, Inc. will provide technical support upon request.

NOTE: *Palladium is only sold to professional stucco applicators who are factory trained and certified to use this product.*

LIMITED WARRANTY

PALLADIUM Textured Coating is warranted for a period of five (5) years from the date of manufacture when installed by a TRAINED AND CERTIFIED PROFESSIONAL APPLICATOR IN STRICT ACCORDANCE WITH THE MOST CURRENT ISSUE OF THE PALLADIUM TEXTURED COATING APPLICATION MANUAL PUBLISHED BY SEALANTS & COATINGS TECHNOLOGIES, INC. Additionally, the Warranty Agreement must be signed by the owner, professional applicator and the General Contractor and the original returned to SCT within 45 days after completion of application. Exceptions: This Warranty does not cover failures due to the following:

Fire, flood, natural disaster or any act of God; improper storage, handling, installation or application; plumbing leaks, faulty construction or structure settling that exceeds the material's elasticity.

The SCT Commitment - If PALLADIUM Textured Coating is proved to have failed during the warranty period set forth in the Application Manual, SCT will replace the failed material FOB its nearest distribution point. SCT reserves the right to inspect the job site by an authorized representative prior to the settlement of any claims. Notification of any claims must be made in writing to SCT upon discovery. SCT's sole and complete responsibility for proved material failure is as set forth in this warranty. SCT will not be responsible for incidental, indirect or consequential damages including reinstallation labor. No other warranty is implied or expressed. Questions concerning this Limited Warranty should be directed to SCT. The user is solely responsible to determine the suitability of this product for its intended use prior to application. User assumes all risk and liability in connection therewith.

PHYSICAL PROPERTIES		TEST STANDARDS <small>PALLADIUM Textured Coating System meets or exceeds the following test standards:</small>		
		TEST	METHOD	CRITERIA
Solids Content, %	70	Component Performance and Accelerated Weathering	ASTM G-53	No deleterious effect after 3,000 hours when viewed under 5x magnification.
Ph, as packaged	8.5	Freeze/Thaw	ASTM C-67	No deleterious effect after 300 cycles
Density, lbs/U.S. gal.	9.7	Water Resistance	Tappi T433 Lm8t	5+ hours
Specific Gravity	1.16	Moisture Vapor Transmission	Tappi T433 Lm8t	Average 3+ perms
Minimum Film Forming Temp.	32°F	Tensile Adhesion	ASTM C-297	No adhesive loss
Glass Transition Temperature (Tg)	-17°F	Flame Spread	ASTM E-84	UBC Class 1, NFPC Class A
Storage Stability	Protect from freezing	Smoke Density	ASTM E-84	45 less than red oak
Applicable EPA restrictions on VOC	Complies with standard requirements.	Salt Spray Resistance	ASTM 8117	No deleterious effect after 300 hours
		Mildew Resistance	ASTMD-3273	No growth supported within 28 days
		Fire Endurance	ASTM E119	No effect on fire rating of wall assembly
		Elongation	ASTM D-638	25%
		Tensile Strength	ASTM D-638	210 psi
		Toxicity	LABC Div. 61	Passed